

## Underlay Technical Specification

Item Code: TADK080013

Issue Date: 22/03/2019

Issue No. 8

### Sponge Rubber

**Suitable for underfloor heating**

**Suitable for the stretch-fit installation of carpets**

**End Use Classification (BS 5808: 1991 / BS EN 14499 : 2015): L/U, Luxury Use**



#### Standard Specifications

Nominal square weight	4238 g/m <sup>2</sup> (125 oz/yd <sup>2</sup> )	
Nominal roll weight	46.6 kg (102 lb)	
Nominal roll area	10.96m <sup>2</sup> (1.33m x 8.24m)	
Nominal thickness	8.30mm	ISO 1765

#### BS 5808: 1991 / EN14499 : 2015

End Use Classification	L/U, Luxury Use	
Work of compression (Min. 50 J/m <sup>2</sup> Max. 200 J/m <sup>2</sup> )	150 J/m <sup>2</sup>	BS 4098 & ISO 2094
Retention of work of compression (min 40%)	98 %	BS 4098 & ISO 2094
Compression after dynamic loading	4.6 mm	BS 4098 & ISO 2094
Loss in thickness after dynamic loading (max 15%)	2.5%	BS 4052 & ISO 2094
Loss in thickness after static loading (max 15%)	3.0 %	ISO 3415/3416 & BS 4939
Breaking strength (length/width) min. 30N	182N / 126N	EN ISO 13394 BS 2576
Extension under force (length/width) max. 15% @ 30N	2.2 % / 1.0 %	EN ISO 13394 BS 2576
Resistance to cracking (not greater than 50mm)	Pass	EN 14499 & BS 5808


#### Flammability

Hot metal nut test (tested in Interfloor laboratory)	Low radius of effects of ignition	BS 4790 & BS 5287
--	-----------------------------------	-------------------

#### Other Specifications

Odour	No objectionable odour	
Antimicrobial and mildew resistant	Yes	
Colour / backing	Black / printed Textron® backing	
Packaging	Cream film / blue prin	
Thermal resistance	0.80 togs	BS 4745
Impact sound reduction (Delta Lw)	42 dB †	BSEN ISO 140-8: 1998 and BSEN ISO 717-2: 1997
Emissions (US Carpet & Rug Institute)	Meets low VOC emission criteria	

#### Certificatio



#### Guarantee

Guaranteed for the serviceable lifetime of the carpet when used in accordance with the End Use Classification

#### Notes

\* The nominal roll dimensions have been quoted. These may vary slightly but will comply with the requirements of BS EN 14499:2015

† Value derived from similar product test results