

Floorfixx fini 8 mm: 10 x 85 x 59 cm (5,015 m²)

Art. nr - 62074

estillon
WE WILL IMPROVE YOUR FLOOR

Scan this QR code to view this product on our website.



Description

Floorfixx fini is an underlay system that absorbs small irregularities in the subfloor. Using the self-adhesive lip-seam connection, you can quickly and easily create a new, insulating, and level subfloor that can be loaded immediately. Floorfixx fini is suitable for residential and light project applications. It renovates poor basic floors for LVT Click, vinyl, and LVT Rigid with underlay.

- No waiting/drying times and can be loaded immediately
- Self-adhesive lip-seam connection
- Levels out irregularities
- Maximum stability

Floorfixx fini 8 mm: 10 x 85 x 59 cm (5,015 m²)

Art. nr - 62074



- Extends the lifespan of the finished floors
- Insulates impact sound and meets the 10dB standard set by the VvE

Floorfixx fini 8 mm: 10 x 85 x 59 cm (5,015 m²)

Art. nr - 62074

estillon
WE WILL IMPROVE YOUR FLOOR

Specifications

Floor type	LVT Click / Vinyl / LVT Rigid with underlayment
Product weight	2552 gr/m ² (10% margin)
Product dimensions (Length)	850 mm (10% margin)
Product dimensions (Width)	590 mm (10% margin)
Product dimensions in m2	5,015 m ²
Sound-reducing - ΔL_{lin}	10 dB ΔL_{lin}
Sound-reducing - ΔL_{lin} - Test method	ISO 10140 / ISO 717-2
Base unit	Pack
Thickness	8 mm (10% margin)
Density	319 kg/m ³ (10% margin)
Brand	Floorfixx
Formaldehyde (Test method: EN 120)	E-1
Leveling capacity	Good
Thermal resistance - R-value	0,213 m ² K/W
TOG rating	2,13 TOG
Thermal resistance - Test method	ISO 8302
PC (Punctual Conformability)	12
CS	CS1
CS/CC (compressive Strength / Compressive Creep)	149 kPa
Domestic use	Yes

Floorfixx fini 8 mm: 10 x 85 x 59 cm (5,015 m²)

Art. nr - 62074

estillon
WE WILL IMPROVE YOUR FLOOR

Project use	Yes
Laying method	Floating
TUV certificate	Yes
Type of base floor	Wooden floor / Fixed sand cement floor / Floating screed
Bending strength (Test method: EN 310)	39 N/mm ²
Wheelchair load (Test method: EN 985)	Suitable
Sound-reducing - ΔL_w	21 dB ΔL_w
Sound-reducing - ΔL_w - Test method	ISO 10140 / ISO 717-2
Flame-retardant	Efl-S1
Flame-retardant - Test method	EN 13501-1
CS/CC (Compressive Strength / Compressive Creep)	149 kPa

Floorfixx fini 8 mm: 10 x 85 x 59 cm (5,015 m²)

Art. nr - 62074

estillon
WE WILL IMPROVE YOUR FLOOR

