

Egalsoft 6,5 mm: 22 x 1,37 m (30,14 m²)

Art. nr - 68240

estillon
WE WILL IMPROVE YOUR FLOOR

Scan this QR code to view this product on our website.



Description

Egalsoft® is a unique anti-slip underlay that ensures a durable and easy installation. The carpet underlay is an impregnated nonwoven material with a treated anti-slip surface. Egalsoft® is applicable for both residential and commercial installations. It provides luxury and comfort while extending the lifespan of the carpet. It features high indentation recovery and a removable system, making it perfect when nails or glue are not permitted. Additionally, it offers good sound reduction (27 dB) and thermal insulation. It is easy to cut and quick and simple to install.

Egalsoft 6,5 mm: 22 x 1,37 m (30,14 m²)

Art. nr - 68240

estillon
WE WILL IMPROVE YOUR FLOOR

Specifications

Floor type	Carpet
Thickness	6.5 mm (10% margin)
Product weight	850 g/m ² (10% margin)
Density	131 kg/m ³ (10% margin)
Type of base floor	Wooden floor / Fixed sand cement floor / Floating screed
Domestic use	Yes
Project use	Yes
Wheelchair load (Test method: EN 985)	Suitable
Sound-reducing - ΔL_w	27 dB ΔL_w
TOG rating	2.2 TOG
Thermal resistance - R-value	0.22 m ² K/W
Flame-retardant	Efl-S1
VOC label	A+
Green choice label	Yes
DIBT certificate	Z-158.10-98
Brand	Egalsoft
Laying method	Stretching / single-sided bonding / double-sided bonding
Product dimensions (Length)	22 m (10% margin)
Product dimensions (Width)	1.37 m
Product dimensions in m ²	30.14 m ²
Base unit	Roll

Egalsoft 6,5 mm: 22 x 1,37 m (30,14 m²)

Art. nr - 68240

Material	Top layer: PP Spunbond / Middle layer: impregnated nonwoven / Bottom layer: anti-slip treated layer
Sound-reducing - ΔL_w - Test method	ISO 10140-3:2010
Dimensional stability tensile strength / Long / MD	> 7.0
Dimensional stability tensile strength / Long / MD - unit	kN/m
Dimensional stability tensile strength / Long / MD - Test method	DIN EN 10319
Dimensional stability tensile strength / Cross / CD	> 20.0
Dimensional stability tensile strength / Cross / CD- unit	kN/m
Dimensional stability tensile strength / Cross / CD - Test method	DIN EN 10319
Dimensional stability elongation / stretch / Long / MD	> 50

Egalsoft 6,5 mm: 22 x 1,37 m (30,14 m²)

Art. nr - 68240

estillon
WE WILL IMPROVE YOUR FLOOR

