



REACTION TO FIRE CLASSIFICATION REPORT N° 2021/220

According to EN 13501-1 (2018)

Notification by the French Government to the European Commission
under n° NB 2401
Regulation (UE) n° 305/2011

Sponsor : INTERFLOOR LTD
BROADWAY
HASLINGDEN LANCASHIRE BB4 4LS
UNITED KINGDOM

Product name : AXMINSTER AX 1028A with DURAFIT 500 underlay

Description : Textile floor covering (EN 1307 family)
(see detailed description in paragraph 2)

Date of issue : 22/10/2021

The indicated classification does not prejudice the conformity of marketed materials with the samples submitted to the tests and under no circumstances, this document should not be considered as type approval or certification of the product in the sense of the L 115-27 article of the consumption's code of the law dated June 3rd 1994.

*The reproduction of this classification report is only authorised in its integral form.
It comprises 4 pages*

1. Introduction

This classification report defines the classification assigned to the above-mentioned product (s) in accordance with the procedures given in the NF EN 13501-1 standard: September 2018.

2. Details of classified product**2.1. Product standard**

NF EN 14041 (2005): "Resilient, textile and laminate floor coverings - Essential characteristics".

2.2. Product description

AXMINSTER AX 1028A : Woven Axminster cut pile carpet with patterns (EN 1307 family).

Use surface : 80% wool – 20% polyamide

Type of backing : polyester – polypropylene with coating latex

Nominal mass per unit area : 2148 g/m²

Nominal total thickness : 10,1 mm

Nominal total pile thickness : 7,4 mm

Flame retardant : No

DURAFIT 500 underlay .:

Nominal mass per unit area : 2100 g/m²

Nominal total thickness : 5,25 mm

Installation : AXMINSTER AX 1028A carpet tested glued on DURAFIT 500 underlay.

Together tested glued over a fibre-cement board classified A2_{fl}-s1 with a density (1800 ± 200) kg/m³ and thickness (20 ± 2) mm.

Type of glue : Acrylic glue with depositing 350 g/m².

3. Test reports and tests results in support of this classification**3.1. Tests reports**

Name of laboratory	Name of sponsor	Test report N°	Test method
C.R.E.T.	INTERFLOOR LTD BROADWAY HASLINGDEN LANCASHIRE BB4 4LS UNITED KINGDOM	RL 2021/660-1	NF EN ISO 9239-1 (EN ISO 9239-1 :2010)
		RL 2021/660-2	NF EN ISO 11925-2 (EN ISO 11925-2 :2010)

3.2. Tests results

Test method	Product	Number of tests	Results	
			Parameters	Compliance parameters
NF EN ISO 11925-2	AXMINSTER AX 1028A with DURAFIT 500 underlay	6	Fs ≤ 150 mm	Compliant
Surface exposure-15 secondes			Ignition of the filter paper	Compliant

Test method	Product	Number of tests	Parameters	Results
				Continuous parameters : mean value
NF EN ISO 9239-1	AXMINSTER AX 1028A with DURAFIT 500 underlay	3	Critical heat flux (kW/m ²)	8,1
			Smoke (% X min)	263,1

4. Classification and field of application

4.1. Reference of classification

This classification has been carried out in accordance with EN 13501-1 (2018).

4.2. Classification

Fire behaviour		Smoke production
B _{f1}	-	s1

Classification : B_{f1} – s1

4.3. Field of application

This classification is valid for the following end use applications :

Together tested glued on any A2-s1,d0 or A1 class substrate with a density ≥ 1350 kg/m³.

This classification is valid for the following product parameters :

“AXMINSTER AX 1028A carpet”

- A nominal mass per unit area of : 2148 g/m²
- A nominal thickness of : 10,1 mm
- A nominal pile thickness of : 7,4 mm

“DURAFIT 500 underlay”

- A nominal mass per unit area of : 2100 g/m²
- A nominal thickness of : 5,25 mm

5. Limitations

This classification document does not represent type approval or certification of the product.

“The classification assigned to the product in this report is appropriate to a declaration of conformity by the manufacturer within the context of system 3 of AVCP and CE marking under the Regulation 305/2011/EU of the European Parliament and of the Council of 9 March 2011 laying down harmonised conditions for the marketing of constructions products.

The manufacturer has made a declaration, which is held on file. This confirms that the products design requires no specific processes, procedures or stages (no addition of flame-retardants, limitation of organic content, or addition of fillers) that are aimed at enhancing the fire performance in order to obtain the classification achieved. As a consequence the manufacturer has concluded that system 3 attestation is appropriate.

The test laboratory has, therefore, played no part in sampling the product for the test, although it holds appropriate references, supplied by the manufacturer, to provide for traceability of the samples tested.”

Head of Test
David VANDIERDONCK



For the SARL C.R.E.T.
The Technical Director
Marc WELCOMME



End of the classification report